



MACHINERY and EQUIPMENT

Thermoinsulating hose

Density 0.20 g/cm³, EPDM, sulfur cure / hot air cure

Guide formulation of Exxon	RRS 37
Vistalon 8800	115.0
FEF N-550	30.0
Grundöl AP/E Core 2500 (ex Flexon 815)	85.0
SILLITIN Z 86	60.0
Zinc oxide	8.0
Stearic acid	0.5
PEG 3350	2.0
Calcium oxide	2.0
Sulfur	1.5
MBT 80 %	1.3
Rhenogran CLD-80	1.1
ZDBC	1.0
Rhenogran Geniplex-70	1.7
Rhenogran ZAT-70	1.5
Genitron AC4	3.0
Genitron OB	4.0
Total phr	317.6

To get a density of 0.1 g/cm³, the amount of blowing agent can be increased (up to 5 phr Genitron OB and 8 phr Genitron AC4).

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.