GUIDE FORMULATION || page 1 of 1



Painting material Rubber paint, water-based, black highly elastic coating for all kind of rubber parts

Basis Vinyl acetate

| | | | A 10102.2 [11] |
|-------------|----------------------------|-----|----------------|
| Component A | Demineralized water | | 13.90 |
| | Butyl glycol | | 2.30 |
| | Propylene glycol | | 2.30 |
| | Calgon N neu | (1) | 0.14 |
| | Byk-035 | (2) | 0.28 |
| | Metolat 388 | (3) | 0.42 |
| | Caustic soda solution 50 % | | 0.07 |
| Component B | Aerosil COK 84 | (4) | 0.45 |
| | Levanylschwarz C-LF | (5) | 4.31 |
| | SILLITIN Z 86 | (6) | 8.80 |
| | Sipernat 820 A | (4) | 1.85 |
| Component C | Mowilith DM 2 H | (7) | 63.10 |
| | Byk-035 | (2) | 0.30 |
| | Demineralized water | | 1.78 |
| | Total % by weight | | 100.00 |

Mixing - charge component A

- add and disperse component B

- complete by component C

Suppliers (1) BK Giulini

(2) Byk Chemie

(3) Münzing Chemie

(4) Evonik Industries

(5) Lanxess

(6) HOFFMANN MINERAL

(7) Celanese Emulsions

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

