

**Painting material****Rubber paint, water-based, light-colored****highly elastic coating for all kind of rubber parts****Basis** Vinyl acetate

		A 10201.2 [10]
Component A	Demineralized water	11.70
	Butyl glycol	1.15
	Propylene glycol	1.15
	Calgon N neu (1)	0.15
	Byk-035 (2)	0.30
	Metolat 388 (3)	0.45
	Caustic soda solution 50 %	0.07
Component B	Aerosil COK 84 (4)	0.48
	Kronos 2310 (5)	4.65
	SILLITIN Z 89 (6)	11.50
Component C	Mowilith DM 2 H (7)	68.10
	Byk-035 (2)	0.30
	Total % by weight	100.00

Mixing

- charge component A
- add and disperse component B
- complete by component C

Suppliers

- (1) BK Giuliani
- (2) Byk Chemie
- (3) Münzing Chemie
- (4) Evonik Industries
- (5) Kronos International
- (6) HOFFMANN MINERAL
- (7) Celanese Emulsions

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.