















AUSWAHLKRITERIEN IN ELASTOMEREN

Produkt	Basismaterial	Funktionalisierung	Schwefel/Schwefelspender	Metalloxid	Harz, IIR	Peroxid, Strahlung	NR, SBR, BNR, IR, NBR, HNBR (teilydriert), CR, IIR, CIIR, BIIR	HNBR (vollhydriert), CM, CSM, EPM, EVM	EPDM	FKM, ACM, AEM (VamacO)	Silikon-Compounds	PU-Elastomere
 AKTISIL AM	SILLITIN Z 86	Amino	•	•		•	•	•	•	•		(•)
 AKTISIL MAM	SILLITIN V 88	Methacryl			•	•	•	•	•			
 AKTISIL MAM-R	SILLITIN V 85	Methacryl			•	•	•	•	•			
 AKTISIL MM	SILLITIN Z 86	Mercapto	•	•	•		•		•			
 AKTISIL PF 216	SILLITIN Z 86	Tetrasulfan	•	•	•		•		•			
 AKTISIL PF 777	SILLITIN Z 86	Alkyl	•	•	•	•	•	•	•			
 AKTISIL Q	SILLITIN V 90*	Methacryl			•	•	•			•	•	
 AKTISIL VM 56	SILLITIN Z 86	Vinyl			•	•		•	•			
 AKTISIL VM 56/89	SILLITIN Z 89	Vinyl				•		•	•			
 AKTIFIT AM	SILFIT Z 91	Amino	•	•	•	•	•	•	•	•		•
 AKTIFIT PF 111	SILFIT Z 91	Alkyl	•	•	•	•	•	•	•	•		
 AKTIFIT PF 115	SILFIT Z 91	Amino	•	•	•	•	•	•	•	•		
 AKTIFIT Q	SILFIT Z 91	Methacryl			•	•		•	•	•	•	
 AKTIFIT VM	SILFIT Z 91	Vinyl			•	•		•	•	•	•	

* interne Produktqualität